

KRAFTFIX PU PRIMER 110

ONE-COMPONENT POLYURETHANE PRIMER / JEDNOSKŁADNIKOWY POLIURETANOWY PRIMER



ENG

PROPERTIES AND PURPOSE:

One-component polyurethane primer. It is used as a primer to improve adhesion on surfaces such as concrete, mortar, wood.

- EXCELLENT ADHESION BETWEEN GLUE AND SUBSTRATE
- FAST BONDING TIME

INFORMATION ABOUT THE PRODUCT:

Color of the product: yellowish to brown

Preparation and application: surface should be clean, solid, dry, pressure resistant, cleaned from dust and grease. Apply the primer evenly using a short-pile roller or a fine paintbrush. If the surface is highly absorbant, apply primer in two layers. Second layer apply on dry first layer (3 hours). Parquet should be glued onto the prepared surface within 24 to 72 hours using only reactive adhesives such as KRAFTFIX PU 101, PU 170 2K, EPU 190 2K and 160 HYBRID

Consumption: approx. 180 – 230 g/m² depending on absorbtion and roughness of surface and way of application

Application temperature: optimal working temperature +18°C to +25°C with max. relative air humidity 60%. Do not use under +15°C

Allowed moisture content in concrete: The substrate humidity when laying parquet must not exceed 2.00%. However, with the application of KRAFTFIXPU PRIMER 110, the surface can contain up to a maximum of 2.50% moisture.

Drying time: 3h

Recommended use: interior

Suitable for: it is used as a primer to improve the adhesion on the surfaces such as concrete, mortar, wood

Storage: originally closed and correctly stored product, protected from direct sunlight, in dry room, at temperatures +5°C to +30°C

Packaging: 5kg

POL

WŁAŚCIWOŚCI I ZASTOSOWANIE:

Jednoskładnikowy grunt poliuretanowy. Służy jako podkład poprawiający przyczepność na powierzchniach takich jak beton, zaprawa, drewno.

- DOSKONAŁA PRZYPNOCNOŚĆ POMIĘDZY KLEJEM A PODŁOŻEM
- SZYBKIE CZAS ŁĄCZENIA

INFORMACJE O PRODUKCIE:

Kolor produktu: żółtawy do brązowego

Przygotowanie i aplikacja: Powierzchnia powinna być czysta, solidna, sucha, odporna na nacisk, oczyszczona z kurzu i tłuszczu. Nałóż grunt równomiernie za pomocą wałka o krótkim włosiu lub drobnego pędzla. Jeśli powierzchnia jest bardzo chłonna, nałóż grunt w dwóch warstwach. Druga warstwa powinna być nałożona na suchą pierwszą warstwę (po 3 godzinach). Parkiet należy przykleić do przygotowanej powierzchni w ciągu 24 do 72 godzin, używając tylko klejów reaktywnych, takich jak KRAFTFIXPU 101, PU 170 2K, EPU 190 2K i 160 HYBRID.

Zużycie: ok. 180 – 230 g/m² w zależności od chłonności i chropowatości powierzchni oraz sposobu aplikacji

Temperatura aplikacji: optymalna temperatura robocza to +18°C do +25°C przy maksymalnej wilgotności względnej powietrza 60%. Nie stosować poniżej +15°C

Dozwolona wilgotność betonu: Wilgotność podłoża podczas układania parkietu nie może przekraczać 2,00%. Jednakże, przy zastosowaniu KRAFTFIXPU PRIMER 110, powierzchnia może zawierać do maksymalnie 2,50% wilgoci.

Czas schnięcia: 3h

Zalecane zastosowanie: wnętrza

Odpowiedni do: stosowania jako podkład poprawiający przyczepność na powierzchniach takich jak beton, zaprawa, drewno

Przechowywanie: produkt przechowywać w oryginalnym, dobrze zamkniętym opakowaniu, chronionym przed bezpośrednim światłem słonecznym, w suchym pomieszczeniu, w temperaturze od +5°C do +30°C

Opakowanie: 5kg

Product benefits

